

PRODUCT DESCRIPTION

BF PRINT SUBLI+ is a printable heat transfer vinyl for inkjet and sublimation printers with a smooth, matte finish.

The paper support facilitates the weeding process. After cutting and weeding, the product can be placed on the garment by taking it with the BF MYLAR, which must then be removed hot or with manual withdrawal.

It is recommended to let it dry for 8 hours before cutting.

APPLICATION STEPS

- Print - do not mirror
- Cut - 60° blade
- Weed excess material
- Apply BF MYLAR - remove air bubbles
- Remove from liner
- Turn on your heat press - heat to 285°F
- Place your graphic on the shirt
- Press it - 285°F for 15 seconds
- Remove BF MYLAR - hot

SIZES






8.5" x 11"	Letter
11" x 17"	Tabloid
20" x 27"	Roll

SAFETY NOTICE




The values reported in this document are average values as tested under normal conditions in our lab. We cannot provide a guarantee regarding the information above mentioned in this page. Due to possible variations in the production of garments, B-FLEX recommends testing the material prior to all applications.

Rev_2021/09






TECHNICAL DATA

	Film: polyurethane
	Thickness: 130μ
	Liner: self-adhesive polyester
	Finish: matte
	Inks: inkjet, sublimation

PLOTTER SETTING

	Cut settings: do not mirror
	Blade: 60°
	Minimum cut: 1 cm

APPLICATION

	Temperature: 285°F (300°F for Nylon)
	Time: 15" (20" for Nylon)
	Liner removal: hot (cold with app tape)
	Pressure: medium - 3,5 bar - 50 PSI
	Textile: organic, synthetic, mixed

WASH RESISTANCE

First wash after application	wait 12 hours
Max wash temperature*	30°C - 86°F
Bleach	✗
Dryer	✓

*Temperatures related on heat transfer vinyl; for the inks features, refer to the data sheet inks producer's.